


Ounces	Inches	mm	Irons
1/2	0.0078	0.20	0.4
1	0.0156	0.40	0.8
1 1/2	0.0234	0.60	1.1
2	0.0313	0.79	1.5
2 1/2	0.0391	0.99	1.9
3	0.0469	1.19	2.3
3 1/2	0.0547	1.39	2.6
4	0.0625	1.59	3.0
4 1/2	0.0703	1.79	3.4
5	0.0781	1.98	3.8
5 1/2	0.0859	2.18	4.1
6	0.0938	2.38	4.5
6 1/2	0.1016	2.58	4.9
7	0.1094	2.78	5.3
7 1/2	0.1172	2.98	5.6
8	0.1250	3.18	6.0
8 1/2	0.1328	3.37	6.4
9	0.1406	3.57	6.8
9 1/2	0.1484	3.77	7.1
10	0.1563	3.97	7.5
10 1/2	0.1641	4.17	7.9
11	0.1719	4.37	8.3
11 1/2	0.1797	4.56	8.6
12	0.1875	4.76	9.0
12 1/2	0.1953	4.96	9.4
13	0.2031	5.16	9.8
13 1/2	0.2109	5.36	10.1
14	0.2188	5.56	10.5
14 1/2	0.2266	5.75	10.9
15	0.2344	5.95	11.3
15 1/2	0.2422	6.15	11.6
16	0.2500	6.35	12.0
16 1/2	0.2578	6.55	12.4
17	0.2656	6.75	12.8
18	0.2813	7.14	13.5
19	0.2969	7.54	14.3
20	0.3125	7.94	15.0
21	0.3281	8.33	15.8
22	0.3438	8.73	16.5
23	0.3594	9.13	17.3
24	0.3750	9.53	18.0
25	0.3906	9.92	18.8
26	0.4063	10.32	19.5
27	0.4219	10.72	20.3
28	0.4375	11.11	21



Irons	Inches	mm	Ounces
5	0.1042	2.65	6.7
5 1/2	0.1146	2.91	7.3
6	0.1250	3.18	8.0
6 1/2	0.1354	3.44	8.7
7	0.1458	3.70	9.3
7 1/2	0.1563	3.97	10.0
8	0.1667	4.23	10.7
8 1/2	0.1771	4.50	11.3
9	0.1875	4.76	12.0
9 1/2	0.1979	5.03	12.7
10	0.2083	5.29	13.3
10 1/2	0.2188	5.56	14.0
11	0.2292	5.82	14.7
11 1/2	0.2396	6.09	15.3
12	0.2500	6.35	16.0
12 1/2	0.2604	6.61	16.7
13	0.2708	6.88	17.3
13 1/2	0.2813	7.14	18.0
14	0.2917	7.41	18.7
14 1/2	0.3021	7.67	19.3
15	0.3125	7.94	20.0
15 1/2	0.3229	8.20	20.7
16	0.3333	8.47	21.3
16 1/2	0.3438	8.73	22.0
17	0.3542	9.00	22.7
18	0.3750	9.53	24.0
19	0.3958	10.05	25.3
20	0.4167	10.58	26.7
21	0.4375	11.11	28.0
22	0.4583	11.64	29.3
23	0.4792	12.17	30.7
24	0.5000	12.70	32.0
25	0.5208	13.23	33.3
26	0.5417	13.76	34.7
27	0.5625	14.29	36.0
28	0.5833	14.82	37.3

Not aligned with Ounces chart

According to Federal Test Method
Standard No. 311 – 1101:
1 (leather) ounce = 1/64" [~0.4 mm]
1 (leather) iron = 1/48" [~0.53 mm]

Leather Thickness Chart